

TEXTTEST AG, Zürich/Switzerland

Test Report


Style: FELT
Reference: CD

Date: 13.10.2006, 10:53:08
Instrument: FX 3360 PORTAIR, s/n 111


Material: Standard
Test pressure: 125 Pa
T-Factor: 1.00

Test area: 20 cm²
Test point density: 5'000 %
Orifice: 1.6 mm, s/n 10003

Air Permeability



FFT (1024, Rectangle, 0 %)



Average:	3.82 cfm	CV:	8.2 %	Error (+/-):	0.0 / 24.5 %
Minimum:	2.94 cfm	Cpk:	0.230	Tests:	1'950
Maximum:	4.33 cfm				

Comment: